



TECHNICAL DATA SHEET

Natural Latex High Ammonia / Natural Latex Low Ammonia

SECTIONI: STANDARS

PROPERTIES	TEST METHOD	LIMITS	UNITS
Total colid content (TSC)	ISO 124	–	–
Dry rubber content (DRC)	ISO 126	Min 60.0	% w/w
Non rubber solids content (NRS)	_____	Max 1.7	% w/w
Number of volatile fatty acids*	ISO 506	Max 0.06	–
KOH Index	ISO 127	Max. 0.7	–
pH	ISO 976	Min. 10	–
Total alkalinity as ammonia (NH ₃)	ISO 125	Max. 0.29 (LATZ) / Min. 0.60 (HA)	% w/w
Mechanical stability (MST)*	ISO 35	Min 650	s
Viscosity	ISO 1652	–	cP
Coagulum content	ISO 706	Max 0.03	% w/w
Color (visual inspection)	–	White. Not gray or blue coloration	–
Odor (Boric acid neutralization)	–	Non putrefactive odor.	–

* Limit could change depending on client necessities and/or process variables.



SECTION II: PACKAGING

Bulk, in a 20 000 kg pipe or tank car.

- Flexitank, containing 21 500 kg (in a 20' dry container).
- Plastic drum, containing 205 kg

SECTION III: PRECAUTIONS

Avoid any risk following the guidelines in the product SDS.

SECTION IV: STORAGE

- a. Keep containers closed to avoid possible coagulation.
- b. Avoid heat.

VALEX GROUP LLC 235 Alpha Drive, Suite 206 Pittsburgh, PA 15238 info@valexgroup.com